



Prediction of Compressive Strength of Geopolymer Fiber Reinforced Concrete Using Machine Learning

Kumar, P.¹, Sharma, S.² and Pratap, B.^{3*}

¹ Assistant Professor, Department of Civil Engineering, Mohan Babu University (SVEC), Tirupati, Andhra Pradesh, India.

² Ph.D. Candidate, Department of Civil Engineering, National Institute of Technology Jamshedpur, Jharkhand, India.

³ Assistant Professor, Department of Civil Engineering, Graphic Era (Deemed to be University), Dehradun, Uttarakhand, India.

© University of Tehran 2024

Received: 11 Sep. 2023;

Revised: 2 Jan. 2024;

Accepted: 16 Mar. 2024

ABSTRACT: Geopolymers represent a cutting-edge class of inorganic materials that provide a sustainable substitute for conventional cement and concrete. Through meticulous combinations and ratios of elements like Fly Ash (FA), silica fume, Ground Granulated Blast Slag (GGBS), alkaline solutions, aggregates, superplasticizers, and fibers, geopolymer concrete mixes are generated as part of the experimental program. The investigation concentrates on predicting the 28-day compressive strength, a pivotal parameter in assessing concrete performance. The dataset comprises 96 data points, and two advanced techniques, namely Support Vector Regression (SVR) and Artificial Neural Networks (ANN), are harnessed for this research. The ANN demonstrates an R^2 value of 0.992 on the training dataset, indicating its capacity to elucidate around 99.2% of the variability. On the other hand, SVR boasts an R^2 value of 0.995, signifying an ability to account for about 99.5% of the variance. When applied to the testing data, the ANN achieves an R^2 of 0.96, while SVR attains an R^2 of 0.99. This study suggests that SVR exhibits slightly superior performance in elucidating variance within the testing dataset.

Keywords: ANN, Fly Ash, GGBS, Soft Computing.

1. Introduction

Reinforced Concrete (RC) is a global construction material used worldwide, supported by a substantial global cement production, estimated to be approximately 4.6 Gigatons (Gt) in 2015. Despite its widespread use and durability, RC structures can face challenges over time due to various factors, such as environmental exposure, chemical attack, or structural damage caused by external events (Jindal et

al., 2023). Interventions are often necessary to maintain the load-carrying capacity and extend the service life of existing RC structures. Over the last few decades, externally bonded composite materials have emerged as an effective solution for rehabilitating and enhancing RC structures.

Among these materials, Fiber-Reinforced Cementitious Matrix (FRCM) composites have gained significant attention as an alternative to traditional Fiber-Reinforced Polymer (FRP)

* Corresponding author E-mail: bheempratapbind009@gmail.com

composites (D'Antino et al., 2014; Tayeh et al., 2021; Wong, 2022). Both FRCMs and FRPs consist of continuous high-strength fibers embedded within a matrix, but they differ in the composition of the matrix material (Wang et al., 2009). Furthermore, FRCMs exhibit excellent compatibility with concrete, which promotes a strong bond between the composite material and the existing structure (Carloni et al., 2015).

Alkali-activated materials are a diverse group of inorganic materials that include a novel category known as geopolymers (Qaidi et al., 2022). These materials not only provide alternatives to traditional cement-based products but also mitigate environmental impacts by reusing industrial byproducts and reducing carbon emissions (Kumar et al., 2023). Polypropylene fibers (Althoey et al., 2023; Tayeh et al., 2022) are commonly utilized to control cracking in concrete, but they may not be ideal for geopolymer composites due to this weak interaction. Steel fibers are a popular choice for reinforcing cementitious composites.

Steel fibers' tensile strength and ultimate elongations can vary significantly, ranging from 310-2850 MPa and 0.5-3.5%, respectively (Al-Majidi et al., 2017; Sukontasukkul et al., 2018; Wang et al., 2018). The corrugated surface enhances the interaction between the steel fibers and the binder, improving the composite material's performance and strength (Wang et al., 2018; Yin et al., 2015). One significant application of recycled synthetic fibers lies in the construction industry, offering an effective solution for disposing of commonly consumed plastics like Polyethylene Terephthalate (PET) and Polypropylene (PP) on a global scale (Siddique et al., 2008). Among the synthetic fibers used in construction PP, Polyvinyl Alcohol (PVA), Polyethylene (PE), and PET are the most prevalent ones (Farooq et al., 2019; Mastali et al., 2018; Ranjbar et al., 2016; Sukontasukkul et al., 2018). PP, derived from the monomeric C_3H_6 , is a cost-effective option with inert characteristics in high PH cementitious environments

(Farooq et al., 2019). It helps control plastic shrinkage cracking in concrete and allows for easy dispersion (Larena and Pinto 1993). It has drawbacks such as poor thermal resistance, low modulus of elasticity, and difficulty in forming a strong bond with cementitious matrices due to its inherent hydrophobic nature (Banthia and Gupta 2006; Mu et al., 2002; Yin et al., 2015). On the other hand, PET fibers, produced by recycling PET bottles, exhibit mechanical properties comparable to PP and nylon fibers while being more cost-effective and environmentally friendly to produce (Ochi et al., 2007).

Soft Computing (SC) is an effective approach for addressing complex problems, particularly when mathematical models struggle to express relationships among parameters. SC offers a notable advantage in solving nonlinear and linear problems by accommodating intricate relationships that may be challenging to model mathematically (Ghanbari et al., 2017). A key strength of SC lies in its ability to incorporate human-based knowledge, recognition, understanding, and learning into computational processes (Vadel et al., 2019). In recent years, researchers have increasingly harnessed Artificial Intelligence (AI) methods and Machine Learning (ML) techniques as integral components of SC in predicting various properties of concrete. AI and ML, as sub-branches of SC, bring advanced computational capabilities to the forefront (Shariati et al., 2022). However, accurately predicting the compressive strength of Geopolymer Concrete (GPC) poses challenges due to the significant influence of physical and chemical variables.

Fortunately, AI and ML have emerged as promising solutions to enhance accuracy and efficiency in predicting concrete strength (Naghizadeh et al., 2022). While traditional regression methods lacked accuracy, ML methodologies have significantly improved predictions, the advanced techniques such as Genetic Engineering Programming (GEP), SVR,

ANN, and ensemble approaches (Sahu et al., 2023). SVR constructs hyperplanes that best separate data points based on their features, enabling it to make precise predictions (Li et al., 2022; Shariati et al., 2022). Its ability to handle high-dimensional data and capture nonlinear relationships has made SVR a popular choice in concrete strength estimation.

Inspired by the human brain's functioning, ANN is a deep learning technique capable of learning and generalizing from large datasets (Kaveh and Khavaninzadeh, 2023). As ANN layers process and transform input data, the model comprehensively understands the relationships between variables, leading to highly accurate predictions. Ensemble approaches combine multiple models to improve predictive accuracy by leveraging the strengths of individual algorithms (Huang et al., 2023).

The primary aim of the current research is to create models that can predict experimental data by utilizing two specific techniques: SVR and ANN. The focus of this study is centered around geopolymers concrete, a unique type of concrete made from components such as FA, silica fume, GGBS, as well as Polyvinyl Alcohol Fiber (PVA) and steel fiber. To evaluate the effectiveness of the prediction models (SVR and ANN), the parameter chosen for analysis is the compressive strength of the geopolymers concrete after a curing period of 28 days.

This 28-day compressive strength is a critical indicator of the concrete's

performance and durability. By using the SVR and ANN models, the study aims to establish accurate predictions of this compressive strength based on the specific combinations of materials used in the geopolymers concrete.

2. Materials and Data Demonstrations

The experiment involves the development of a novel type of concrete called geopolymers hybrid fiber-reinforced concrete. This concrete is designed to have enhanced strength and durability by combining various materials and fibers. The main components used in this experiment are FA, Silica fume, GGBS, alkaline solutions, fine and coarse aggregates, superplasticizers, and a hybrid combination of steel fiber and PVA fiber. Concrete relies on binding agents to ensure that its components are properly linked together.

In addition to binding materials, concrete also contains fine and coarse aggregates like sand and gravel. The experimental program involves creating different concrete mixes by varying the proportions of these materials. The specific combinations and ratios of FA, Silica fume, GGBS, alkaline solutions, aggregates, superplasticizers, and hybrid fibers are detailed in Table 1 of the experiment. This mix design is a roadmap for producing batches of geopolymers hybrid fiber-reinforced concrete with consistent and controlled properties. ML approaches necessitate a diverse set of input variables (Wang et al., 2018). These input variables and the corresponding outputs are derived from an experimental program.

Table 1. Mix design of the experimental program

Mix designations	P0S1	P0S2	P0S3	P1S4	P1S0	P2S0	P3S0	P4S0
FA	585	585	585	585	585	585	585	585
Silica fume	32.5	32.5	32.5	32.5	32.5	32.5	32.5	32.5
GGBS	32.5	32.5	32.5	32.5	32.5	32.5	32.5	32.5
Na ₂ SiO ₃	156	156	156	156	156	156	156	156
NaOH	104	104	104	104	104	104	104	104
Fine aggregate	850	850	850	850	850	850	850	850
Coarse aggregate	800	800	800	800	800	800	800	800
Super plasticizer	10	10	10	10	10	10	10	10
Polyvinyl alcohol fiber	0	0	0	0	0.10%	0.20%	0.30%	0.40%
Steel fiber	0.10%	0.20%	0.30%	0.40%	0	0	0	0

*P1S0: is Polyvinyl alcohol fiber 0.1% and Steel fiber 0%.

This specific study focuses primarily on predicting the 28-day compressive strength, a critical parameter for evaluating concrete performance. The models employed for this purpose involve a selection of input variables, and their correlation with the 28-day compressive strength is investigated.

The chosen input variables encompass a variety of factors that contribute to the properties of the concrete mixture. These variables include cement, water, sand, coarse aggregate, superplasticizer, silica fume, FA, alkali/binder ratio, steel fiber, and PVA fiber. Each of these variables plays a distinct role in shaping the characteristics of the final concrete product.

The dataset used in this study comprises 96 data points, each representing a specific combination of input variables and the corresponding 28-day compressive strength. These data points serve as the basis for training and testing the ML models. Table 2 presents a comprehensive summary of the statistical analysis conducted on the input variables. The statistics presented in the table include the mean, standard deviation, minimum value, and maximum value for each input variable. These statistics collectively offer a thorough understanding of the variability and central tendencies within the input dataset.

3. Methodology

In this study, ML models were employed to estimate the compressive strength of a

material, and these models were implemented using Python code through the Anaconda software platform. Anaconda Navigator is a hub for accessing Python and other programming languages crucial for data science and machine learning applications. It emphasizes activities like package development and maintenance to support these tasks effectively. The study employed three distinct techniques, namely ANN and SVR, to predict the compressive strength of a material. These techniques are widely used in ML for regression tasks, where the goal is to predict a continuous numerical output.

To assess the accuracy of the predictions generated by these models, the R^2 was utilized. The R^2 value is a metric that ranges from 0 to 1, with higher values indicating better alignment between the predicted outcomes and the actual measured values. Furthermore, the study conducted rigorous evaluations to gauge the models' performance. This involved statistical checks and error assessments, including Mean Absolute Error (MAE) and Root Mean Squared Error (RMSE). These metrics offer insights into how well the models' predictions align with the actual data by measuring the average magnitude of errors. A lower MAE and RMSE indicate better predictive accuracy and a smaller deviation between predicted and actual values. The data set is generated from the experimental programs. The process involved organizing a dataset into two subsets: a training set and a test set.

Table 2. Statistical description of input variables

	Total	Mean	SD	Min.	25%	50%	75%	Max.
FA	96	552.5	26.67	520	520	552.50	585	585
GGBS	96	48.75	13.34	32.5	32.5	48.75	65	65
Silica fume	96	48.75	13.34	32.50	32.50	48.75	65	65
NaOH	96	110.6	14.61	91	100.50	110.50	120.3	130
Na ₂ SiO ₃	96	165.75	21.92	136.50	151.13	165.75	180.4	195
Coarse aggregate	96	850	0	850	850	850	850	850
Fine aggregate	96	800	0	800	800	800	800	800
alk/b	96	0.425	0.056	0.35	0.3875	0.425	0.46	0.50
Superplasticizer	96	10	0	10	10	10	10	10
Polyvinyl alcohol fiber	96	0.125	0.14	0	0	0.05	0.2	0.40
Steel fiber	96	0.125	0.14	0	0	0.05	0.2	0.40
Compressive strength	96	38.81	8.56	21.56	32.26	38.46	44.25	58.8

In the 70-30 data split, a dataset is partitioned into two subsets: 70% is allocated for training a model, and the remaining 30% is reserved for testing the model's performance. Each example in these sets was broken down into individual instances of input features, also known as independent variables, which were associated with a specific target or dependent variable to be predicted. The input features utilized in this analysis were chosen to represent quantifiable aspects that experiments could measure. These features were carefully defined and structured to provide an advantageous learning environment for the various models being evaluated (Figure 1). This structured setup ensured that the models could learn effectively from the data.

The ANN underwent a process of manual fine-tuning to achieve a reasonable level of accuracy in predicting the target variable. This fine-tuning process involved adjusting the model's internal parameters and architecture to minimize prediction errors and enhance performance. Subsequently, the hyper parameters of the ANN were determined based on the outcomes of this initial manual fine-tuning (Pratap et al., 2023). Hyper parameters are settings external to the model but influence

its learning process. SVR aims to find the optimal function that best captures the underlying patterns in the data while maintaining a certain margin of error. The fundamental idea is to identify a hyperplane that effectively fits as many data points as possible within a specific epsilon (ϵ) tube, where the goal is to minimize the deviation of data points from the predicted values while allowing for a controlled tolerance.

SVR employs a mathematical approach to determine the optimal hyperplane by solving a constrained optimization problem. One of the strengths of SVR is its ability to handle non-linear relationships between variables by utilizing kernel functions. These functions transform the original feature space into a higher-dimensional space, enabling the algorithm to capture complex patterns that might not be apparent in the original data.

4. Results and Discussions

The study evaluates the predictive accuracy of the ANN model by comparing its predicted outcomes to the actual measured compressive strengths. The analysis involves two main aspects: the statistical comparison pattern and the model's performance metrics.




Fig. 1. An input and output roadmap for the ANN and SVR algorithms

In terms of statistical analysis, the study assesses the pattern of outcomes obtained from the actual testing of geopolymer concrete samples and the predictions made by the ANN and SVR models. The R^2 value serves as an indicator of how well the model's predictions match the actual data. In this case, the R^2 value of 0.9924 for training and 0.9672 for testing signifies an excellent performance of the ANN model in accurately calculating the compressive

strength outcomes. Figures 2a and 3a visually represent these high R^2 values, highlighting the closeness of the model's predictions to the real data points. On the other hand, Figures 2b and 3b provide a graphical depiction of the distribution of the investigated outcomes compared to the estimated outcomes by the ANN model. These figures allow for a direct comparison, revealing the model's efficacy in capturing the trend of the actual outcomes.




Fig. 2. a) Relation between experimental and predicted values for training model of ANN; and b) Distribution of experimental, predicted and error values for training model of ANN




Fig. 3. a) Relation between experimental and predicted values for a testing model of ANN; and b) Distribution of experimental, predicted and error values for a testing model of ANN

The study also addresses the errors associated with the ANN model's predictions. This study analyzes the spread of errors in terms of the largest, lowest, and average error values. For the training phase, the largest error is 2.003 MPa, the lowest error is 0.0314 MPa, and the average error is 0.5646 MPa. Similarly, for the testing phase, the largest error is 3.69 MPa, the lowest error is 0.028 MPa, and the average

error is 1.356 MPa. The SVR model demonstrates exceptional performance in accurately predicting compressive strength outcomes, as evidenced by high R^2 values of 0.9985 (Figure 4a) for training and 0.9908 (Figure 5a) for testing. These values highlight the strong alignment between the model's predictions and actual data points. This closeness between predicted and real values is visually represented in Figures 4.




Fig. 4. a) Relation between experimental and predicted values for training model of SVR; and b) Distribution of experimental, predicted and error values for training model of SVR




Fig. 5. a) Relation between experimental and predicted values for the testing model of SVR; and b) Distribution of experimental, predicted and error values for a testing model of SVR

Conversely, Figures 4b and 5b visually illustrate how the SVR model's estimated outcomes compare to the investigated outcomes. This direct comparison underscores the model's ability to capture the underlying trends in the actual data (Li et al., 2022). The study also delves into the errors associated with the SVR model's predictions, examining their distribution (Sahu et al., 2023). The analysis of error distribution entails the consideration of the largest, smallest, and average error values.

During the training phase, the most significant error observed is 1.164 MPa, while the smallest error is 0.00053 MPa, and the average error is 0.1389 MPa. Similarly, in the testing phase, the largest error amounts to 2.287 MPa, the smallest error is 0.152 MPa, and the average error is 1.0366 MPa. Table 3 presents the performance metrics of two different machine learning algorithms, ANN and SVR, on a dataset. These metrics are commonly used to evaluate the quality of predictive models. This column simply lists the two machine learning algorithms being compared, which are ANN and SVR. These are different techniques used for regression tasks, where the goal is to predict a continuous numerical output. The ANN has an R^2 of 0.992 on the training set, indicating it explains about 99.2% of the variance, and SVR has an R^2 of 0.995, indicating it explains about 99.5% of the variance. Both values are very high, suggesting strong performance on the training data. ANN has an RMSE of 0.73, while SVR has an RMSE of 0.32. Lower RMSE values indicate better model accuracy, so SVR is performing better on the training data in this regard.

ANN has an MAE of 0.56, and SVR has an MAE of 0.13. Again, lower MAE values indicate better accuracy, and SVR has a lower MAE, suggesting better performance on the training data. ANN has an R^2 of 0.96 on the testing data, while SVR has an R^2 of

0.99, indicating that SVR performs slightly better in terms of explaining variance in the testing data. ANN has an RMSE of 1.65, and SVR has an RMSE of 0.81. Again, lower RMSE values are better, so SVR outperforms ANN on the testing data. ANN has a MAE of 1.35, while SVR has a MAE of 0.53. Like RMSE, lower MAE values indicate better accuracy, and SVR is more accurate on the testing data.

5. Conclusions

This research successfully demonstrated the development of geopolymers concrete through a combination of fibers, FA, and GGBS as precursor materials. Elaborate prediction studies were conducted involving partial replacement of FA with GGBS and silica fume. The conclusions drawn from the results and interpretations can be summarized as follows:

- The performance of the prediction models is assessed using the coefficient of determination (R^2). The ANN achieves an R^2 of 0.992 on the training set, explaining approximately 99.2% of the variance, while the SVR obtains an R^2 of 0.995, explaining about 99.5% of the variance. On the testing data, the ANN's R^2 is 0.96, whereas the SVR's R^2 is 0.99. This indicates that SVR slightly outperforms ANN in terms of explaining variance in the testing data.
- The analysis of error distribution involves assessing the largest, smallest, and average error values. During the training phase, the most significant error observed is 1.164 MPa, while the smallest error is 0.00053 MPa, and the average error is 0.1389 MPa. Similarly, in the testing phase, the largest error amounts to 2.287 MPa, the smallest error is 0.152 MPa, and the average error is 1.0366 MPa.

Table 3. Training and testing results data

Algorithms	Training			Testing		
	R^2	RMSE	MAE	R^2	RMSE	MAE
ANN	0.992	0.73	0.56	0.96	1.65	1.35
SVR	0.995	0.32	0.13	0.99	0.81	0.53

- Overall, both models demonstrate strong performance on the training data, with SVR having a slight advantage in terms of RMSE and MAE. However, when applied to unseen testing data, SVR maintains its superior performance in terms of RMSE, MAE, and R-squared, suggesting that SVR is the more suitable model for this specific dataset. The importance of evaluating a model's performance on both training and testing data is highlighted by the results presented in this table.

6. References

- Al-Majidi, M.H., Lampropoulos, A. and Cundy, A.B. (2017). "Steel fibre reinforced geopolymer concrete with improved microstructure and enhanced fibre-matrix interfacial properties", *Construction and Building Materials*, 139, 286-307, <https://doi.org/10.1016/j.conbuildmat.2017.02.045>.
- Althoey, F., Zaid, O., Alsulamy, S., Martínez-García, R., de Prado-Gil, J. and Arbili, M.M. (2023). "Experimental study on the properties of ultra-high-strength geopolymer concrete with polypropylene fibers and nano-silica", *PLoS One*, 18(4), e0282435, <https://doi.org/10.1371/journal.pone.0282435>.
- Banthia, N. and Gupta, R. (2006). "Influence of polypropylene fiber geometry on plastic shrinkage cracking in concrete", *Cement and concrete Research*, 36(7), 1263-1267, <https://doi.org/10.1016/j.cemconres.2006.01.010>.
- Carloni, C., Antino T.D., Sneed, L.H. and Pellegrino, C. (2015). "Role of the matrix layers in the stress-transfer mechanism of frcm composites bonded to a concrete substrate", *Journal of Engineering Mechanics*, 141(6), [https://doi.org/10.1061/\(ASCE\)EM.1943-7889.0000883](https://doi.org/10.1061/(ASCE)EM.1943-7889.0000883).
- D'Antino, T., Carloni, C., Sneed, L.H. and Pellegrino, C. (2014). "Matrix-fiber bond behavior in pbo frcm composites: a fracture mechanics approach", *Engineering Fracture Mechanics*, 117, 94-111, <https://doi.org/10.1016/j.engfracmech.2014.01.011>.
- Farooq, M., Bhutta, A. and Banthia, N. (2019). "Tensile performance of eco-friendly ductile geopolymer composites incorporating different micro-fibers", *Cement and Concrete Composites*, 103, 183-192, <https://doi.org/10.1016/j.cemconcomp.2019.05.004>.
- Ghanbari, M., Hadian, A.M., Nourbakhsh, A.A. and Mackenzie, K.J.D. (2017). "Modelling and optimization of compressive strength and bulk density of metakaolin-based geopolymer using central composite design: A numerical and experimental study", *Ceramics International*, 43(1), 324-335, Elsevier, <https://doi.org/10.1016/j.ceramint.2016.09.159>.
- Huang, Y., Huo, Z., Ma, G., Zhang, L., Wang, F. and Zhang, J. (2023). "Multi-objective optimization of fly ash-slag based geopolymer considering strength, cost and co2 emission: A new framework based on tree-based ensemble models and nsga-II", *Journal of Building Engineering*, 68, 106070, Elsevier Ltd, <https://doi.org/10.1016/j.jobbe.2023.106070>.
- Kaveh, A. and Khavaninzadeh, N. (2023). "Efficient training of two Ann's using four meta-heuristic algorithms for predicting the FRP strength", *Structures*, 52, 256-272, <https://doi.org/10.1016/j.istruc.2023.03.178>.
- Kumar, P., Pratap, B., Sharma, S. and Kumar, I. (2023). "Compressive strength prediction of fly ash and blast furnace slag-based geopolymer concrete using convolutional neural network", *Asian Journal of Civil Engineering*, <https://doi.org/10.1007/s42107-023-00861-5>.
- Jindal, A., RN, G., Kumar, P., Kumar, V. and Rana, D. (2023). "Rehabilitation prospects of concrete pavements with self-compacting concrete containing wollastonite micro fibre", *Civil Engineering Infrastructures Journal*, 56(2), 221-233, <https://doi.org/10.22059/ceij.2023.341456.1828>.
- Larena, A. and Pinto, G. (1993). "The effect of surface roughness and crystallinity on the light scattering of polyethylene tubular blown films", *Polymer Engineering and Science*, 33(12), 742-747, <https://doi.org/10.1002/pen.760331204>.
- Li, Y., J., Shen, Lin, H., Li, H., Lv, J., Feng, S. and Ci, J. (2022). "The data-driven research on bond strength between fly ash-based geopolymer concrete and reinforcing bars", *Construction and Building Materials*, 357, (100), 129384, <https://doi.org/10.1016/j.conbuildmat.2022.129384>.
- Mastali, M., Dalvand, A., Sattarifard, A.R., Abdollahnejad, Z. and Illikainen, M. (2018). "Characterization and optimization of hardened properties of self-consolidating concrete incorporating recycled steel, industrial steel, polypropylene and hybrid fibers", *Composites Part B: Engineering*, 151, 186-200, <https://doi.org/10.1016/j.compositesb.2018.06.021>.
- Mu, B., Meyer, C. and Shimanovich, S. (2002). "Improving the interface bond between fiber mesh and cementitious matrix", *Cement and Concrete Research*, 32(5), 783-787,

- [https://doi.org/10.1016/S0008-8846\(02\)00715-9](https://doi.org/10.1016/S0008-8846(02)00715-9).
- Naghizadeh, H., Saadat, M., Basirat, S. and Iranpour Mobarakeh, M. (2022). "Performance improved multi-objective optimization in applying low-impact development strategies to control urban runoff", *Civil Engineering Infrastructures Journal*, 56(2), 257-276, <https://ceij.ut.ac.ir/article88680.html>.
- Ochi, T., Okubo, S. and Fukui, K. (2007). "Development of recycled pet fiber and its application as concrete-reinforcing fiber", *Cement and Concrete Composites*, 29(6), 448-455, <https://doi.org/10.1016/j.cemconcomp.2007.02.002>.
- Pratap, B., Shubham, K., Mondal, S. and Hanumantha, B. (2023). "Exploring the potential of neural network in assessing mechanical properties of geopolymers incorporating fly ash and phosphogypsum in pavement applications", *Asian Journal of Civil Engineering*, 24, 3575-3589, <https://doi.org/10.1007/s42107-023-00735-w>.
- Qaidi, S.M.A., Sulaiman Atrushi, D., Mohammed, A.S., Unis Ahmed, H., Faraj, R.H., Emad, W., Tayeh, B.A. and Mohammed Najm, H. (2022). "Ultra-high-performance geopolymer concrete: A review", *Construction and Building Materials*, 346, 128495, <https://doi.org/10.1016/j.conbuildmat.2022.128495>.
- Ranjbar, N., Mehrali, M., Behnia, A., Javadi Pordsari, A., Mehrali, M., Alengaram, U.J. and Jumaat, M.Z. (2016). "A comprehensive study of the polypropylene fiber reinforced fly ash based geopolymer", *PLoS One*, (W. Batchelor, ed.), 11(1), e0147546, <https://doi.org/10.1371/journal.pone.0147546>.
- Sahu, A., Kumar, S. and Shrivastav, A.K.L., Pratap B. (2023). "Machine learning approach to study the mechanical properties of recycled aggregate concrete using copper slag at elevated temperature", *Asian Journal of Civil Engineering*, 25, 911-921, <https://doi.org/10.1007/s42107-023-00821-z>.
- Shariati, M., Mafipour, M.S., Ghahremani, B., Azarhomayun, F., Ahmadi, M., Trung, N.T. and Shariati, A. (2022). "A novel hybrid extreme learning machine-grey wolf optimizer (elm-gwo) model to predict compressive strength of concrete with partial replacements for cement", *Engineering with Computers*, 38(1), 757-779, <https://doi.org/10.1007/s00366-020-01081-0>.
- Siddique, R., Khatib, J. and Kaur, I. (2008). "Use of recycled plastic in concrete: A review", *Waste management*, 28(10), 1835-1852, <https://doi.org/10.1016/j.wasman.2007.09.011>.
- Sukontasukkul, P., Pongsopha, P., Chindaprasirt, P. and Songpiriyakij, S. (2018). "Flexural performance and toughness of hybrid steel and polypropylene fibre reinforced geopolymer", *Construction and Building Materials*, 161, 37-44, <https://doi.org/10.1016/j.conbuildmat.2017.11.122>.
- Tayeh, B.A., Akeed, M.H., Qaidi, S. and Bakar, B.H.A. (2022). "Influence of microsilica and polypropylene fibers on the fresh and mechanical properties of ultra-high performance geopolymer concrete (uhp-gpc)", *Case Studies in Construction Materials*, 17, e01367, <https://doi.org/10.1016/j.cscm.2022.e01367>.
- Tayeh, B.A., Zeyad, A.M., Agwa, I.S. and Amin, M. (2021). "Effect of elevated temperatures on mechanical properties of lightweight geopolymer concrete", *Case Studies in Construction Materials*, 15, <https://doi.org/10.1016/j.cscm.2021.e00673>.
- Vadel, M., Khadija, B., Nawal, Z. and Mohamed, S. (2019). "Modelling compressive strength of moroccan fly ash - phosphogypsum geopolymer bricks", *SN Applied Sciences*, 1(12), 1-9, <https://doi.org/10.1007/s42452-019-1736-1>.
- Wang, R., Gao, X., Zhang, J. and Han, G. (2018). "Spatial distribution of steel fibers and air bubbles in uhpc cylinder determined by x-ray ct method", *Construction and Building Materials*, 160, 39-47, <https://doi.org/10.1016/j.conbuildmat.2017.11.030>.
- Wang, X.H., Jacobsen, S., He, J.Y., Zhang, Z.L., Lee, S.F. and Lein, H.L. (2009). "Application of nano indentation testing to study of the interfacial transition zone in steel fiber reinforced mortar", *Cement and Concrete Research*, 39(8), 701-715, <https://doi.org/10.1016/j.cemconres.2009.05.002>.
- Wong, L.S. (2022). "Durability performance of geopolymer concrete: a review", *Polymers*, 14(5), 868, <https://doi.org/10.3390/polym14050868>.
- Yin, J., D'Haese, C. and Nysten, B. (2015). "Surface electrical properties of stainless steel fibres: An afm-based study", *Applied Surface Science*, 330, 65-73, <https://doi.org/10.1016/j.apsusc.2014.12.188>.



This article is an open-access article distributed under the terms and conditions of the Creative Commons Attribution (CC-BY) license.